

# Development of an $8 \times 8$ CPW Microwave Kinetic Inductance Detectors (MKIDs) Array at 0.35 THz

Jing Li<sup>1,2,\*</sup>, J.P. Yang, S. Li, D. Liu, Z.H. Lin S.C. Shi, S. Mima, N. Furukawa and C. Otani

<sup>1</sup>Purple Mountain Observatory (PMO), CAS, China

<sup>2</sup>Key Laboratory of Radio Astronomy (KLRA), CAS, China

<sup>3</sup>Institute of Physical and Chemical Research (RIKEN), Japan

\*Contact: lijing@pmo.ac.cn, phone +86-25-8333-2204

**Abstract**—Microwave Kinetic Inductance Detectors (MKIDs) are rather promising for THz direct detector arrays of large size, particularly with simple frequency-division multiplexing. Purple Mountain Observatory is developing a terahertz superconducting imaging array (TeSIA) for the DATE5 telescope to be constructed at Dome A, Antarctica. Here we report on the development of a prototype array for the TeSIA project, namely an  $8 \times 8$  CPW MKIDs array at 0.35THz. The array consists of 64-pixel superconducting resonators in the frequency range of 4-5.575 GHz with an interval of 0.025 GHz and 64-pixel twin-slot antennas at 0.35 THz for coupling THz radiation to the detector array. Based on our design, we fabricate the MKIDs array using TiN superconducting film with  $T_c$  about 4.5 K. And the performance is characterized at different temperatures. Detailed results and analysis will be presented.

## I. INTRODUCTION

China is planning to construct an observatory at Dome A, Antarctica, which has been found to be the best site (with low perceptible water vapor and low atmospheric boundary layer) on the earth for THz and Optical/IR astronomy. One of the telescopes to be built there is a 5-m THz telescope (DATE5 [1]) targeting at 350 $\mu$ m and 200 $\mu$ m atmospheric windows. One science case for the DATE5 is to observe extreme starburst galaxies at different redshifts to better understand the nature and evolution of these enigmatic and important objects. Therefore, we are going to develop an imaging camera with 1024-pixel. We are currently developing a detector array demonstrator to meet such a requirement in the future [2].

The detector array demonstrator has  $8 \times 8$  pixels and will work at 0.35 THz, which is chosen to demonstrate the performance of the detector array on a small sub-millimeter telescope (POST, with a diameter of 30cm) situated at Delingha, China. As is well known, microwave kinetic inductance detectors (MKIDs [3]) use frequency domain multiplexing that allows thousands of pixels to be read out over a single microwave transmission line followed by a cryogenically cooled low noise amplifier. Furthermore, a large number of MKIDs can be integrated like a filter bank to realize on-chip spectrometers such as DESHIMA and SuperSpec [4, 5]. Hence we choose MKIDs to develop our detector array demonstrator. The MKIDs make use of TiN superconducting films with a critical temperature of

approximately 4.5 K, which can be operated at temperatures of  $\sim 0.3$ K [6]. Furthermore, TiN MKIDs can reach a noise equivalent power (NEP) below  $1 \times 10^{-19}$  W/Hz<sup>0.5</sup>, which is a sufficiently high sensitivity for ground-based astronomical observations [6]. The  $8 \times 8$  TiN MKIDs will be integrated with a micro-lens array of  $8 \times 8$  0.95-mm hyper-spherical Si lens with a separation of 2 mm between individual lens. The readout for this MKIDs detector array demonstrator is similar to others, but adopting a commercial arbitrary wave-function generator to generate 64-tone input signal. The 0.3K refrigerator for the demonstrator is a He3 two-stage sorption cooler (CRHe7 [7]) based on a liquid helium cryostat, which offers over 10 hours continuous cooling with a total heat load of up to 20  $\mu$ W. In this paper, we mainly introduce the design, fabrication, and characterization of the  $8 \times 8$  TiN MKIDs.

## II. MKIDS: DESIGN AND FABRICATION

We adopted the coplanar-waveguide (CPW) type resonator to design our  $8 \times 8$  TiN MKIDs array because it has a relatively simple architecture of only one thin-film layer on the substrate. This kind of resonator has a quarter-wavelength transmission line with one end capacitively coupled to a feed line and the other matched to a planar antenna (twin-slot antenna, for example) [8].

We started from the design of the coupler, which is an elbow structure at the end of the resonator near the feed line. With this layout, we can make the feed line and the coupler share the same metal section as the ground. The CPW line for the coupler was designed to have a 3  $\mu$ m center stripe and 2  $\mu$ m gaps. The ground space between the feed line and the coupler was set as 2  $\mu$ m. Based on the structure, we can get different coupling strength by changing only the length of the coupler. Using an electromagnetic microwave simulator [9], we studied the dependences of the coupling strength upon the coupling quality factor ( $Q_c$ ), the resonance frequency ( $f_i$ ) and the coupler length ( $L_c$ ).

The  $8 \times 8$  MKIDs array was fabricated in the cleanroom of RIKEN Center for Advanced Photonics (Japan). As introduced before, we chose TiN superconducting films for this MKIDs detector array [10, 11]. MKIDs based on TiN superconducting films have a few advantages including a)  $T_c$  can be controlled between  $\sim 0$ -5 K by the components of Ti

and  $N_2$  [6]; b) quasi-particle lifetime is around 10-200  $\mu$ s [6]; c) low loss in the superconducting state [6]. Firstly, a 100-nm thick TiN film was deposited on a high resistivity Si wafer in a DC magnetron sputtering system. Secondly, the CPW lines were defined in contact lithography by a mask aligner. Thirdly, the etching course was done in an ICP machine.

### III. MEASURED PERFORMANCE

For the fabricated  $8 \times 8$  TiN MKIDs array, we mainly measured its Q factors and the dependence of Q factors upon the bath temperature and the input power for the multiplexing readout. The measurements were done simply by a scalar network analyzer to the  $8 \times 8$  TiN MKIDs array and a following 0.1~12 GHz cryogenically cooled low-noise amplifier, which has an equivalent noise temperature of 5 K and gain of approximately 35 dB.

### IV. CONCLUSIONS

We have designed and fabricated an  $8 \times 8$  TiN MKIDs array. Its transmission characteristic has been measured with respect to the bath temperature and input power. The temperature dependence follows that predicted by the Mattis-Bardeen theory, while the resonance frequency and the quality factor are both insensitive to the input power when it is below -40 dBm.

### ACKNOWLEDGMENT

The authors are grateful to Wei Miao and Zheng Lou of Purple Mountain Observatory for the designs of the 3.5 THz twin-slot antenna and the 8x8 micro-lens array. Jing Li would

like to acknowledge the technical assistance on dilution refrigerator cooler during the testing of Wen Zhang of Purple Mountain Observatory.

### REFERENCES

- [1] J Yang, et al., "China's Antarctic observatory," project proposal, 2013.
- [2] S.C. Shi and TeSIA team, "Development of a terahertz superconducting imaging array (TeSIA)," ISSTT2014, Moscow, Russia, Apr. 2014.
- [3] Peter K. Day, Henry G. LeDuc, Benjamin A. Mazin, Anastasios Vayonakis and Jonas Zmuidzinas "A broadband superconducting detector suitable for use in large arrays," *Nature* 425, 817-821, 2003.
- [4] A. Endo, J.J.A. Baselmans, P.P. van der Werf, B. Knoors, S.M.H. Javadzadeh, S.J.C. Yates, D.J. Thoen, L. Ferrari, A.M. Baryshev, Y.J.Y. Lankwarden, P.J. de Visser, R.M.J. Janssen and T.M. Klapwijk, "Development of DESHIMA: A Redshift Machine Based on a Superconducting On-Chip Filterbank," *Proc. SPIE*, Vol. 8452, 2012.
- [5] Erik Shirokoff, et al., "MKID development for SuperSpec: an on-chip, mm-wave, filter-bank spectrometer," *Proc. SPIE*, 8452, 84520R (2012).
- [6] Henry G. Leduc, Bruce Bumble, Peter K. Day, Byeong Ho Eom, Jiansong Gao, Sunil Golwala, Benjamin A. Mazin, Sean McHugh, Andrew Merrill, David C. Moore, Omid Noroozian, Anthony D. Turner and Jonas Zmuidzinas, "Titanium Nitride Films for Ultrasensitive Microresonator Detectors," 2010.
- [7] 0.3K He7 refrigerator, Chase Research Cryogenics, UK.
- [8] R. M. J. Janssen, J. J. A. Baselmans, A. Endo, L. Ferrari, S. J. C. Yates, A. M. Baryshev, and T. M. Klapwijk, "High optical efficiency and photon noise limited sensitivity of microwave kinetic inductance detectors using phase readout," *APL*, 103, 203503, 2013.
- [9] Sonnet Software, Inc.
- [10] Kensuke Koga, Seiichiro Ariyoshi, Mitsuhiro Yoshida, Noboru Furukawa, Masashi Hazumi, and Chico Otani, "Development of TiN MKIDs for CMB polarization observations," *23<sup>rd</sup> International Symposium on Space Terahertz Technology*, 2012.
- [11] K. Koga, S. Ariyoshi, C. Otani, M. Yaoshida, H. Watanabe, M. Hazumi, "Development of TiN-MKIDs for cosmic inflation exploration," 2011.